



PINKBAR™ FIBERGLAS™ REBAR

LESS WEIGHT. MORE STRENGTH™

PINKBAR™ Fiberglass™ Rebar is designed as a cost-effective, lightweight, rust-free reinforcement solution for concrete over traditional steel rebar.

- Designed for use in flatwork/slabs-on-grade, and residential footings and foundation walls.
- Meets physical and mechanical requirements of ASTM D7957 material standard for Solid Round Glass Fiber Reinforced Polymer (GFRP) Bars for Concrete Reinforcement.
- Made with boron-free Advantex® E-CR glass fibers and epoxy resin.
- Proprietary sand coating enables superior bonding with concrete.

Product Advantages Compared to Steel



Less Weight. Less Install Time. Fewer Truckloads.

- Up to 7x LIGHTER than steel**
- Cut install time in half*
 - Save on transportation



Less Overall Cost

From purchase to install, users can save an average of 33% on total-cost compared to steel*



More Strength

PINKBAR™ Fiberglass™ Rebar is 2x stronger in tensile strength compared to the same size diameter of grade 60 steel.



More Durability

PINKBAR™ Fiberglass™ Rebar will never rust, making concrete structures more durable, especially in corrosive environments.

*Based on average estimates of a conventional 6" thick rectangle slab, \$60 per hour labor rate. Pricing and labor rates can vary by region and fluctuations in the market.

**Comparing #3 PINKBAR™ with #4 steel rebar. #3 PINKBAR™ replaces #4 steel rebar in flatwork applications requiring reinforcement for shrinkage crack mitigation.

Proven Performance

ASTM D7957

- PINKBAR™ Fiberglass™ Rebar meets physical and mechanical requirements of ASTM D7957 material standard
- Material Certifications are provided upon request and purchase

ACI 332 & ACI 440

- PINKBAR™ Fiberglass™ Rebar can be used in residential concrete, including footings and foundation walls, as prescribed in ACI 332 using ACI 440 design methodology

ICC-ES AC454

- Meets or exceeds ICC-ES AC 454 acceptance criteria including bond strength, tensile strength, and tensile modulus of elasticity.

*Per PINKBAR™ submittal package pending ICC-ES AC 454 evaluation

Proven Crack Mitigation in Flatwork

Through independent testing, #3 PINKBAR™ has been proven to mitigate shrinkage cracks as effectively as #4 steel in poured slabs and can increase the long-term service life of flatwork due to the non-corrosive properties of fiberglass rebar.*

*Restrained Shrinkage Testing at University of Brescia, Italy, 2020

Applications

PINKBAR™ Fibreglas™ Rebar is intended for use in:

RESIDENTIAL				COMMERCIAL/INDUSTRIAL										
• Driveways	• Sidewalks	• Pool Decks	• Basement Floors	• Basement walls	• Footings	• Concrete Masonry	• ICF Construction	• Parking Slabs	• Warehouse Floors	• Agricultural Slabs	• Loading Docks	• Architectural Precast	• Truck Aprons	• Pour Back Slabs

Physical & Mechanical Properties

Bar Size	NOMINAL DIAMETER		NOMINAL CROSS SECTIONAL AREA		UNIT WEIGHT/LENGTH		GUARANTEED ULTIMATE TENSILE FORCE		GUARANTEED ULTIMATE TENSILE STRENGTH		ULTIMATE TENSILE STRAIN	MEAN TENSILE MODULUS OF ELASTICITY	
	in	mm	in ²	mm ²	lb/ft	kg/m	kip	kN	ksi	MPa	%	Msi	GPa
#2	0.25	6	0.05	32	0.05	0.07	6.76	30.08	138.0	951	2.03%	6.80	46.88
#3	0.375	10	0.11	71	0.11	0.16	15.07	67.03	137.0	945	2.01%	6.80	46.88
#4	0.500	13	0.20	129	0.18	0.27	26.90	119.66	134.5	927	1.98%	6.80	46.88
#5	0.625	16	0.31	199	0.32	0.47	40.30	179.26	130.0	896	1.91%	6.80	46.88

MEAN TRANSVERSE SHEAR STRENGTH		BOND STRENGTH		FIBER MASS CONTENT	MOISTURE ABSORPTION IN 24 H AT 50°C (122°F)	MOISTURE ABSORPTION TO SATURATION AT 50°C (122°F)	MEAN GLASS TRANSITION TEMPERATURE (DSC)	
ksi	MPa	psi	MPa	%	%	%	°F	°C
≥19	≥131	≥1100	≥7.6	≥70	≤0.25	<1.0	≥212	≥100

Handling & Placement

Handling and installation of PINKBAR™ Fibreglas™ Rebar is the same as for steel bars, with a few notes and exceptions:

- Cutting: Do not shear fiberglass bars. Field cut fiberglass bars using a fine blade saw, grinder, and carborundum or diamond blade. Sealing the ends of fiberglass bars is not necessary.
- Chairing: Place chairs at a spacing that ensures adequate concrete cover.
- Tying: Use same tying methods as for steel rebar. Tie wire material based on contractor preference.

As with any reinforcement placement, be sure to follow best practices in all phases of your concrete project, from planning to construction, including pouring, curing, joint cutting, and maintenance for optimal performance.

Packaging

PINKBAR™ Fibreglas™ Rebar ships from multiple locations in the U.S. Master bundles and sub-bundles are available in standard sizes.

BAR SIZE	WEIGHT PER 20 FOOT BAR (lb)	NO. OF BAR PER SUB-BUNDLE	WEIGHT PER SUB-BUNDLE (lb)	NO. OF BARS PER MASTER BUNDLE	WEIGHT PER MASTER BUNDLE (lb)	NO. OF BARS IN A FULL TRUCK LOAD (FTL)	WEIGHT PER FTL (lb/ton)
#2	0.94	50	45	500	450	46,000	42,000/21
#3	2.15	20	42	500	1050	19,000	40,000/20
#4	3.63	10	36	500	1800	12,000	44,000/22
#5	6.26	10	62	250	1550	7,250	44,000/22

Stock bent bars are available on request.

Labeling & Certificates

Production lot certificates are available upon request – traceable by bar marks imprinted on the bar in intervals showing the bar diameter, stock order and production date.

Storage

PINKBAR™ Fibreglas™ Rebar is durable in the outdoor environment. Discoloration, fading or chalking of the surface can occur due to oxidation or UV exposure. However, this is cosmetic only and will not affect the performance of the bar. For prolonged exposure under direct sunlight, protective cover is recommended to minimize these effects.



OWENS CORNING
HOW WE BUILD NOW™

CDOW Wholesale

Stocking Locations: Metro Dallas, Houston, Denver & Nashville
Drop ship direct nationwide to customer warehouses or direct to jobsite
Send us an email at five@cdow.us or visit our website for more info...

www.CDOW.us

CALCULATE SAVINGS IN FLATWORK



This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10023236-G. February 2021. THE PINK PANTHER™ & © 1964–2021 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. The color PINK is a registered trademark of Owens Corning. © 2021 Owens Corning. All Rights Reserved.